



HEAT-X (HX5W73J) Fire Proximity Jacket

FABRIC CERTIFICATION : EN ISO 11612:2015

INDUSTRY		MODEL DESCRIPTION
Metal	Oil & Gas	High collar
Mining	Cement	
Automotive	Heavy Engineering	Press button with velcro adjustment
Power Distribution	Construction	



SPECIAL FEATURES			
IFR	LIGHT WEIGHT	FLEXIBLE	DURABLE

STYLE	FABRIC COMPOSITION	TRIM	MARKING
Jacket	Outer shell: 100% Aluminized Para-aramid (480g/m ² ±5%) Middle shell: Woolen Felt Inner shell: 100% Treated FR Cotton 240 g/m ²	<ul style="list-style-type: none"> 100% Para-aramid Thread FR Velcro Button 	Manufacturer Logo, Model No., Fabric Composition, Certification, Size

FEATURES
Skin friendly fabric
Protection against molten metal
Protection against high radiation heat
FR performance will remain same during the working life
The hi-tech fabric will not cause any itchinness, stiffness


APPLICATIONS
Metal Foundries & smelting operations
Pot Room & Blast Furnace
Casting, Forging & heat treating
Metal Fabrication & Foundry Equipment Maintenance
Energy & Utilities

STORAGE
May be stored in the dark for upto 2 years
Do not store in direct/high heat or sunlight at this may distort the properties of the fabric
Can be stored and transported in their original cartons at ambient temperature

Udyogi



FABRIC COMPOSITION



Outer Shell- Aluminized Para-aramid 480 g/m²

Woolen Felt

Inner Shell- 100% Treated FR Cotton 240 g/m²

100% Para-aramid Thread

COLOUR	AVAILABLE SIZES	CLEANING	PACKING
Silver	S, M, L, XL, XXL	Cleaned dry with a soft brush.	1 pc per packet

EN ISO 11612:2015 - OUTER SHELL

CODE	INSPECTION CHARACTERISTIC	STANDARD	LEVELS
A	Limited Flame spread	ISO 15025	1 (Lowest 1, Highest 3)
B	Convective Heat	ISO 9151	1 (Lowest 1, Highest 3)
C	Radiant Heat	ISO 6942	3 (Lowest 1, Highest 4)
D	Liquid Molten Aluminium	ISO 9185	3 (Lowest 1, Highest 3)
E	Liquid Molten Iron	ISO 9185	3 (Lowest 1, Highest 3)
F	Contact Heat	ISO 12127	1 (Lowest 1, Highest 3)

EN ISO 11612:2015 - INNER SHELL

CODE	INSPECTION CHARACTERISTIC	STANDARD	LEVELS
A	Limited Flame spread	ISO 15025	1 (Lowest 1, Highest 3)
B	Convective Heat	ISO 9151	1 (Lowest 1, Highest 3)
C	Radiant Heat	ISO 6942	1 (Lowest 1, Highest 4)
F	Contact Heat	ISO 12127	1 (Lowest 1, Highest 3)

CARE AND MAINTENANCE

- Chlorine bleach should never be used, this can change in the properties for which the manufacturer can assume no liability.
- Store the Aluminized Jacket by hanging dry in a well ventilated area out of direct sunlight.
- Garments for protection of close approach towards molten metals only.
- The life of garment depends on use & exposure.
- Rubbing against rough or sharp edges is particularly harmful to the outer layer.
- Rough handling, folding and abrasion should be avoided.

Udyogi